



April 28, 2011

Mr. Charles Idowu
CoverTec Products LLC
11041 Springfield Place
Hollywood, FL 33026

Dear Mr. Idowu:

On behalf of the National Floor Safety Institute I would like to thank you for submitting your product for Phase 1 testing. CoverShield Vinyl Guard was tested per the ANSI/NFSI B101.1-2009 Test Method for Measuring Wet SCOF of Common Hard-Surface Floor Materials on April 25, 2011 and the average Static Coefficient of Friction (SCOF) for each sample was 0.87 which exceeds our minimum acceptable wet SCOF value of a 0.6 and is therefore eligible for Phase 2 certification testing.

The purpose of the ANSI/NFSI B101.1-2009 is to determine the wet Static Coefficient Of Friction (SCOF) of hard surfaced flooring materials (ie: ceramic floor tile, vinyl floor coverings, finishes, etc.) using the BOT-3000. The product was tested per Phase 1 of our certification process and does not reflect real-world performance as evaluated in Phase 2 testing. Please feel free to contact us if you have any questions. Thank you.

Sincerely,

A handwritten signature in black ink, which appears to read 'Russell J. Kendzior', is written over a horizontal line.

Russell J. Kendzior
President