



StrongSeal Wetlook

Damp Tolerant UV resistant wet look sealer and joint-sand stabilizer

Product Description

StrongSeal Wetlook is a concentrated damp tolerant two-part polyurethane water dispersed paver sealer and joint stabilizer. When applied to pavers and concrete the product will produce a hard-wearing wet look surface that provides protection against stains and exceptional water resistance. In addition, its properties bond and lock down the sand between paving joints.

Features

- Wet look non-yellowing sealer
- Concentrated longer lasting
- Highly water repellent
- Beautifies and protects faded pavers
- Repels, oil, grease and rust stains
- Resistant to hot tire pickup
- Reduces weed growth
- Voc compliant
- Abrasion resistant
- Makes surface easier to clean
- Mildew and fungi resistant
- Ideal joint-sand stabilizer
- Retards efflorescence

Typical Uses

- Interlocking concrete pavers
- New and old concrete
- Colored and stamp concrete
- Unglazed ceramic tiles - Saltillo
- Paving stones
- Masonry brick
- Natural stone

Color

Milky White Dries Water Clear.

Packaging

5-gallon (19 liter) Kit
2-gallon (7.6 liter) Kit

Shelf Life

12 months when stored at 77°F (25°C) or less in a dry and shaded area. Protect from freezing.

Theoretical Coverage

Porous surface

150 – 200 ft²/ diluted gal (3.7- 4.9 m²/l)

Dense surface

250 - 300 ft²/ diluted gal (6.0 -7.4 m²/l)

A two-coat application is recommended for porous substrates. Each coat should be diluted with water.

Application Properties

Property	Typical Results
Solids by weight	41%
VOC	<50 g/l
Weight per gallon	8.5 lbs
Drying time	0.5 to 3 hours
Odor	Very mild

Compliances

Meets VOC regulations for CA and NY

USDA compliant for use in meat and poultry areas when fully cured.

Surface Preparation

Brick and Concrete Pavers

The surface must be completely free of oil, grease, curing compounds, other coatings, water repellants and any other foreign material that may inhibit the sealer adhesion to it. The surface must be porous enough to allow sealer penetration. Surface can be damp but with no standing water. If there is efflorescence remove by using **PreTreat**. Degrease the floor with **SurfaceClean**. Test for water absorption. If water beads on any section of the floor repeat the process until contaminants are completely removed.

Concrete

Concrete surfaces must be clean and sound. Prepare non-porous surfaces with PreTreat solution or by mechanical means (shot blaster, sand blasting, scarifying, etc. If PreTreat is used, the surface must be flushed with clean water and 1 oz of CT-50 to neutralize the surface.

After cleaning, brush off any ponded water. The surface can be damp but with no standing water prior to sealer application. Allow new concrete to cure for at least 14 days before application.

Mixing

The Mix Ratio is 4Part A to 1 Part B and is pre-measured in container. Add the two parts together and mix for two minutes. **The usable pot life of the mixed material is approximately 90 minutes. Only mix enough material that can all be used within 90 minutes of mixing. Split the quantities in 1/2 if necessary and only mix 1/2 the product at a time.**

Mixed product should NEVER be stored in a closed container

Dilution

DILUTE 1 PART MIXED MATERIAL WITH 1 PART CLEAN WATER. For example, 5 gals of mixed material with 5 gals of water makes 10 gals of sealer ready to use.

Application

StrongSeal may be applied by low pressure sprayer or 3/8th nap roller. Apply one or more coats. EACH COAT SHOULD BE DILUTED. Allow to dry tack free between coats. Apply each coat uniformly using a sprayer. For the first coat apply enough Wetlook to flood the joint which will provide joint stabilization.

Important note

Over application and excess sealer must not be allowed to pool or puddle. Wipe up any pools after 15 minutes. Dry time is approximately 2 hours at 70°F (21°C), but varies depending on temperature, wind and humidity. **Make sure first coat is tack free before applying the second coat.**

Brick and Concrete Pavers

The paver joints should be completely filled with dry, correctly graded jointing sand with the top level not exceeding the bottom of the chamfer of 1/8" below the surface of paver. Ensure the sand has been completely tamped into the paver joints and the application area swept clean.

Dry time

Protect the application from rain for 12 hours. Allow 2 to 3 hours at 70°F (21°C) before opening area to foot traffic. Allow 48 hours at 70°F (21°C) for vehicular traffic

Clean Up

When wet, flush with clean water and baking soda. When dry, clean tools and equipment with CT-12 Thinner.

Limitations

Once mixed product must be used within 90 minutes

Do not apply if surface temperature is below 40°F (4°C) or is expected to fall below 40°F (4°C) within 24 hours. Do not apply if rain is expected within 12 hours of application. Do not add paint thinners, solvents, or admixtures. Do not apply other coatings (epoxy, urethanes, etc.) over this material. Do not install concrete overlays, other toppings or surface treatments over this material. Test area for sealer acceptance and desired results.

Health and Safety

Before using this product consult the Material Safety Data Sheet (SDS). The SDS can be obtained at www.covertecproducts.com

Limited Warranty

This product is warranted to be of good quality and that it complies with the properties shown in its current datasheet. CoverTec will replace or, at our election, refund the purchase price of the product if proven defective when used according to the instructions in the current datasheet. Any suspected defect must be reported to CoverTec in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. CoverTec Products LLC. **makes no warranty as to the merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied and explicitly excludes liability for consequential damages, down time, or delay.**