p: 754.223.2465 • f: 754.223.2467
e: tec@covertecproducts.com
CoverTecProducts.com

GlazeGuard Plus Cleaning & Maintenance Instructions

The most critical procedure for keeping the floor clean is to AGITATE the floor with **EMERALD FLOOR CLEANER /MAINTAINER** solution diluted with water using a **soft bristle brush** followed by EXTRACTION.
The agitation suspends the soil in the water/cleaning solution and the extraction removes the soil from the flooring surface. Removal of the soil prevents it from settling back onto the floor. The AGITATION can be done in many ways including:
1) manually with soft brush or
2) with a 175-RPM floor machine with a soft brush or
3) by employing an auto scrubber with soft brushes. Use a soft brush manually or with a floor machine to clean

NOTE. DO NOT CLEAN GlazeGuard Plus WITH A PAD, AS IT WILL MORE QUICKLY WEAR OFF THE COVERGRIP AGGEGATE

EXTRACTION should immediately follow agitation. Extraction can be done in many ways including:
1) a high quality, commercial wet vac with squeegee or wand
2) an auto scrubber
3) a portable or truck mounted rinse and reclaim system

GlazeGuard Plus Maintenance Tips

1. It is good practice to **Sweep** the entire flooring surface with a soft broom , as frequently as possible to reduce the amount of sand or other abrasive particles that the wear the coating surface.
2. Use chair slides or felt pads as protective bottoms under furniture.
3. Always dilute cleaning solutions according to directions, overuse of detergents can leave a residual film on the floor.
4. **Do not clean the floor with high alkaline, acidic, ammonia based, abrasive cleaners, and/or bleach or products containing bleach**. These chemicals may degrade GlazeGuard Plus, adversely affecting the sheen and stain repellency.
5. Take care not to use pads or overly aggressive brushes otherwise you risk dulling and or scratching the surface.
6. Do not over-wet floor; this will avoid leaving ‘slop marks’ on walls, furniture, carpeting, etc.
7. Always read product label and SDS before using this or any chemical products for proper use, and any recommended personal protective equipment (PPE) such as glasses, gloves, etc.

Repair Instructions for Scratches and Gouges

1. Locate defect to be repaired.
2. Abrade with 220 grit sandpaper to dull the surface.
3. Depending on how large the defect is, you may want to use a rotor machine or a palm sander. Both can be used with a 220-mesh screen.
4. Feather out GlazeGuard surfaces two inches around any bare area
6. The defect should now be removed and the floor smooth.
7. Clean area with a properly diluted solution of a neutral cleaner. Alternatively, can also use rubbing alcohol or xylene to wipe off dust. All residue should be removed, and the surface allowed to dry.
8. Apply the GlazeGuard Plus within 30 mins of the surface drying
9. Before applying product to area see the proper preparation, mixing, and application instructions.

Recoating Instructions

1. If a 2nd coat is required, then recoat GlazeGuard Plus within the first 10 hours of the first coat application.
2. After 10 hours, abrade the entire surface area with 220 grit sandpaper/screen. The objective is to dull the surface ready for a second coat.
3. Clean area with a properly diluted solution of a neutral cleaner. Alternatively rubbing alcohol or xylene can be used to wipe off the dust.
4. All residue should be removed, and the surface allowed to dry.
5. Apply the GlazeGuard Plus within 30 mins of surface drying.
6. Before applying product to area see the proper preparation, mixing, and application instructions.

Soft Nylon Brush Heads





END OF SECTION